



# FAS

FORWARD ACTING SCORED

## The FAS is Oseco's problem-solving rupture disc

- Sizes 1" through 18"
- Standard materials of construction: 316 Series Stainless Steel, Nickel, Inconel® 600, Monel®, and Hastelloy® C
- Excellent for gas or liquid service applications
- Lowest  $K_R$  in the industry means less flow restriction
- $K_{RG}$  0.223  $K_{RL}$  0.19
- Non-fragmenting design
- "Fail-safe" A damaged or incorrectly installed FAS will always burst at less than the rated pressure
- Elevated temperatures up to 900° F
- Burst tolerance  $\pm 5\%$  > 40 psig &  $\pm 2$  psig  $\leq$  40 psig
- Non-torque-sensitive

## FAS

The Oseco FAS (Forward Acting Scored) Rupture Disc is designed and manufactured for high-performance and demanding rupture disc applications.

The FAS is scored after the forming of its high crown. This process yields a high-performance disc to withstand the most difficult applications. The FAS offers a smooth non-scored surface toward the process media. This limits product accumulation on the disc and reduces the risk of polymerization and crystallization of media on the disc surface.


The FAS rupture disc has a 90% operating ratio for applications requiring a high operating to set pressure ratio. Due to the high operating ratio and non-fragmenting design, the FAS rupture disc is an excellent choice for isolation of safety relief valves.

Installing the leak-tight FAS rupture disc between the process media and the safety relief valve protects the valve and prevents emissions to the atmosphere.



- Operates at 90% of stamped burst pressure
- PFA-grade Fluoropolymer liners available for atmospheric and/or process sides

- ASME Approved



### COMMON APPLICATIONS

Safety relief valve isolation - High Pressure

### OPERATING RATIO

90%

### BURST TOLERANCE

$\pm 5\%$  over 40 psig,  $\pm 2$  psig at or below 40 psig

### MANUFACTURING RANGE

0%

**oseco** pressure intelligence

EKOTECH PTY LTD PH: 03 9457 3700 FAX: 03 9457 3800 E: sales@ekotech.com.au

FAS: Minimum / Maximum Burst Pressure @ 72° F (psig) / 22° C (barg)

Size	Materials		316 SS	Nickel	Inconel	Monel	Hast. C-276
1.0" DN 25	Minimum	psig barg	110 7.6	70 4.8	100 6.9	75 5.2	135 9.3
	Maximum	psig barg	4100 282.7	3500 241.3	4000 275.8	3750 258.5	5000 344.7
	To withstand full vacuum	psig barg	220 15.2	140 9.7	200 13.8	140 9.7	270 18.6
	Ring recommended if below	psig barg	475 32.7	350 24.1	400 27.6	350 24.1	550 37.9
1.5" DN 40	Minimum	psig barg	80 5.5	50 3.4	80 5.5	60 4.1	125 8.6
	Maximum	psig barg	4000 275.8	2900 199.9	3900 268.9	3500 241.3	4500 310.3
	To withstand full vacuum	psig barg	160 11.0	100 6.9	170 11.7	120 8.3	250 17.2
	Ring recommended if below	psig barg	350 24.1	250 17.2	300 20.7	275 19.0	400 27.6
2.0" DN 50	Minimum	psig barg	60 4.1	40 2.8	65 4.5	50 3.4	100 6.9
	Maximum	psig barg	3000 206.8	2000 137.9	2500 172.4	2300 158.6	3500 241.3
	To withstand full vacuum	psig barg	120 8.3	80 5.5	130 9.0	100 6.9	200 13.8
	Ring recommended if below	psig barg	270 18.6	180 12.4	225 15.5	200 13.8	300 20.7
3.0" DN 80	Minimum	psig barg	55 3.8	30 2.1	50 3.4	40 2.8	80 5.5
	Maximum	psig barg	2000 137.9	1600 110.3	2100 144.8	1800 124.1	2000 137.9
	To withstand full vacuum	psig barg	110 7.6	60 4.1	100 6.9	80 5.5	160 11.0
	Ring recommended if below	psig barg	200 13.8	145 10.0	225 15.5	175 12.1	250 17.2
4.0" DN 100	Minimum	psig barg	50 3.4	40 2.8	50 3.4	45 3.1	70 4.8
	Maximum	psig barg	2000 137.9	1400 96.5	1800 124.1	1600 110.3	2000 137.9
	To withstand full vacuum	psig barg	110 7.6	80 5.5	100 6.9	90 6.2	140 9.7
	Ring recommended if below	psig barg	200 13.8	125 8.6	175 12.1	150 10.3	250 17.2
6.0" DN 150	Minimum	psig barg	50 3.4	40 2.8	55 3.8	50 3.4	80 5.5
	Maximum	psig barg	1800 124.1	1200 82.7	1600 110.3	1400 96.5	2000 137.9
	To withstand full vacuum	psig barg	100 6.9	80 5.5	110 7.6	100 6.9	160 11.0
	Ring recommended if below	psig barg	125 8.6	125 8.6	125 8.6	125 8.6	175 12.1
8.0" DN 200	Minimum	psig barg	55 3.8	40 2.8	60 4.1	50 3.4	85 5.9
	Maximum	psig barg	1800 124.1	1100 75.8	1300 89.6	1200 82.7	1600 110.3
	To withstand full vacuum	psig barg	110 7.6	80 5.5	120 8.3	100 6.9	170 11.7
	Ring recommended if below	psig barg	125 8.6	125 8.6	125 8.6	125 8.6	175 12.1
10.0" DN 250	Minimum	psig barg	65 4.5	40 2.8	65 4.5	55 3.8	100 6.9
	Maximum	psig barg	1500 103.4	1000 68.9	1200 82.7	1100 75.8	1500 103.4
	To withstand full vacuum	psig barg	130 9.0	80 5.5	130 9.0	110 7.6	200 13.8
	Ring recommended if below	psig barg	125 8.6	125 8.6	125 8.6	125 8.6	175 12.1
12.0" DN 300	Minimum	psig barg	75 5.2	40 2.8	75 5.2	60 4.1	110 7.6
	Maximum	psig barg	1300 89.6	1000 68.9	1100 75.8	1000 68.9	1300 89.6
	To withstand full vacuum	psig barg	150 10.3	80 5.5	150 10.3	120 8.3	220 15.2
	Ring recommended if below	psig barg	125 8.6	125 8.6	125 8.6	125 8.6	175 12.1
14.0" DN 350	Minimum	psig barg	85 5.9	45 3.1	80 5.5	65 4.5	115 7.9
	Maximum	psig barg	1000 68.9	800 55.2	900 62.1	800 55.2	1000 68.9
	To withstand full vacuum	psig barg	170 11.7	90 6.2	160 11.0	130 9.0	230 15.9
	Ring recommended if below	psig barg	-- --	-- --	-- --	-- --	-- --
16.0" DN 400	Minimum	psig barg	90 6.2	50 3.4	85 5.9	70 4.8	120 8.3
	Maximum	psig barg	900 62.1	700 48.3	800 55.2	700 48.3	900 62.1
	To withstand full vacuum	psig barg	180 12.4	100 6.9	170 11.7	140 9.7	240 16.5
	Ring recommended if below	psig barg	-- --	-- --	-- --	-- --	-- --
18.0" DN 450	Minimum	psig barg	95 6.5	50 3.4	85 5.9	70 4.8	125 8.6
	Maximum	psig barg	800 55.2	600 41.4	700 48.3	600 41.4	800 55.2
	To withstand full vacuum	psig barg	190 13.1	100 6.9	170 11.7	140 9.7	250 17.2
	Ring recommended if below	psig barg	-- --	-- --	-- --	-- --	-- --
MAX TEMP	° F ° C	900 482.2	750 398.9	900 482.2	800 426.7	900 482.2	

Maximum Temperature for all materials if Teflon lined is 500 Degrees F.

## Related products

**SENSORS**

AMS  
SVT  
CMS

**HOLDERS**

FRDI  
FRDI-P  
FRDH

## Free Flow Area/Minimum Net Flow Area (MNFA)

Disc Size (Inch)	Net Flow Area (Sq. In.)
1	0.864
1.5	2.036
2	3.355
3	7.393
4	12.73
6	28.89
8	50
10	78.9
12	113.1
14	137.9
16	176.7
18	233.7
24	405.9

## Burst Tolerance

$\pm 5\% > 40$ psig	$\pm 2$ psig $\leq 40$ psig
---------------------	-----------------------------



Let us help you with all your pressure relief questions. Contact Oseco at **800-395-3475** or email us at [info@oseco.com](mailto:info@oseco.com).

**Oseco Inc**

1701 W. Tacoma  
Broken Arrow Oklahoma 74012 USA  
Tel: (918) 258-5626  
Fax: (918) 251-2809

